

CREOSOTE OIL

SCOPE

Creosote Oil Light is a long-lasting wood preservative. On no account must coal tar creosote be used for preservation of the interior timbers of residential properties.

USES

Treatment of all bare timber structures, roofing timbers, railway sleepers, timber for ground and/or water contact, e.g. stakes, poles, fences, other agricultural structures and general use.

CHARACTERISTICS

- * Product reference : Conforms to BSS 144 (1973) Type 2
: Control of Substances Hazardous to Health Regulations (COSHH) 1988
- * Physical Appearance : Light Brown
: Contains: Coal tar creosote 100% w/w
- * Theoretical spread rate : 4- 8 M² /Litre, depending on porosity
- * Drying time : Approximately 3 - 10 minutes at normal temperature, ground immersed timber dip for 1 hour.
- * Solubility-water solubility : Approx. 0.03g/l at 20° C

	Unit	Min.	Max.
* Density at 20° C	: kg/m ³	1050	1150
* Tar acids	: % (v/v)	1.0	3.0
* Crystallisation	: °C	-	-5
* Benz (a) pyrene	: ppm	-	50
* Flash point	: °C	80	-
* Viscosity at 20°C	: mPa's	12	25

STORAGE & HANDLING

- * Storage : Keep containers tightly closed and away from source of heat.
: Store away from open fires and ignition sources.
- * Shelf life : In unopened packing and under normal storage conditions : unlimited.

SURFACE PREPARATION

Ensure the surface is clean, free from all contaminants.

APPLICATION METHOD

Ensure adequate ventilation when applying. Apply two coats allowing first coat to dry before applying second coat. Woodshield Creosote oil is ready for use, can be applied by brushing, dipping or steeping.

WARNING

- Flammable & Harmful product ! Keep out of reach of children.
- Eyes : In the event of accidental splashes, flush eyes with fresh water immediately.
 - Skin : Wash skin thoroughly with soap and water.
 - Inhalation : Remove to fresh air, loosen collar and keep patient rested, obtain medical attention.

GENERAL INFORMATION

The product is manufactured under the supervision of PMC, United Kingdom. The information provided on this data sheet is not indented to be complete and is provided as general advice only. It is the responsibility of the user to ensure the product is suitable for the purpose for which he wishes to use it.

Technical consultancy is always available to ensure optimum specification and performance.



Gulf Membrane & Coating Industries W.L.L.

Post Box 10266 State of Bahrain

Tel: 770019 Fax: 774450 E-Mail: baderco@batelco.com.bh